

HyGold P220N

Paraffinic Base Oil Marketing Specification

This severely hydrotreated paraffinic base oil provides excellent color and consistency. It passes the IP 346 labeling requirement.

TEST DESCRIPTION	TEST METHOD	SPECIFICATIONS		TYPICAL VALUES
		MIN	MAX	
Physical Properties				
Viscosity, SUS at 100°F (37.8°C)	ASTM D2161	205	235	219
Viscosity, SUS at 210°F (98.9°C)	ASTM D2161			48.5
Viscosity, cSt at 40°C (104°F)	ASTM D445	39.8	45.6	42.6
Viscosity, cSt at 100°C (212°F)	ASTM D445			6.6
API Gravity, 60°F (15.6°C)	ASTM D1250			33.1
Specific Gravity, 60°F (15.6°C)	ASTM D4052			0.8598
Viscosity Index	ASTM D2270	95		109
Viscosity-Gravity Constant	ASTM D2501			0.796
Density, lbs/gal at 60°F	ASTM D1250			7.169
Density at 15.6°C, g/cm ³	ASTM D1250			0.8593
Molecular Weight	ASTM D2502			445
Flash Point, COC, °F (°C)	ASTM D92	400 (204)		457 (236)
Flash Point, PMCC, °F (°C)	ASTM D93			433 (223)
Color, ASTM	ASTM D6045		2.0	0.6
Pour Point, °F (°C)	ASTM D5949			2 (-17)
Cloud Point, °F (°C)	ASTM D5773			6 (-14)
Noack Volatility, wt%	ASTM D5800			9.0
Water Content	ASTM D7546M		PASS	PASS
Appearance	ASTM D4176M		PASS	PASS
Chemical Properties				
Acid Number, mg KOH/g	ASTM D664			0.01
Aniline Point, °F (°C)	ASTM D611	225 (107)	248 (120)	242 (117)
Sulfur, ppm	ASTM D7220			4
Health and Safety Properties				
Polycyclic Aromatic Compounds, wt%	IP 346		3	<3
Modified Ames Assay, MI	ASTM E1687		1	<1
FDA Regulation	21 CFR 178.3620 (C)		PASS	PASS

HyGold P220N is a product of Ergon - West Virginia, Inc.
August 13, 2020